



Product Data Sheet

I-BOND[®] OSB FC 4312

I-BOND[®] OSB FC 4312 is a standard functionality reactivity modified diphenyl methane diisocyanate (MDI).

APPLICATION

I-BOND[®] OSB FC 4312 was developed for the use in the production of Oriented Strand Board (OSB) panels as a means of increasing the typical production rate in a composite wood manufacturing facility.

For more information on this product, please contact us at www.ibondwood.com.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	brownish clear liquid		
NCO value	30.8	%	PU/IV-1
Viscosity (25 °C)	250	mPa.s	PU/VIS-1
Acidity	100	ppm	PU/AC-1
Hydrolysable chlorine	<= 2000	ppm	PU/HC-1
Specific gravity (25 °C)	1.23		PU/SPG-1

STORAGE AND HANDLING

Containers of I-BOND[®] OSB FC 4312 should be kept properly closed and stored indoors in a well-ventilated area under normal factory conditions. Storage at temperatures ranging from 20 - 30 °C (68 - 86 °F) provides a convenient viscosity for handling. Storage at low temperature is not recommended because it may lead to some crystallisation; this material must therefore be protected from frost. Storage at temperatures above 50°C is not recommended, since this can lead to the formation of insoluble solids and also the viscosity build-up increases on extended storage. Under the recommended storage conditions and if protected from humidity and contaminants, i.e. in properly sealed drums, cans, etc., I-BOND[®] OSB FC 4312 has a storage life of 6 months at the customer.

In case of storage in bulk containers, please contact our Sales representative for further details. Detailed information on how to obtain optimum bulk storage conditions, is available in the ISOPA document Guidelines for Safe Loading/Unloading, Transportation & Storage of TDI and MDI. Reaction with atmospheric moisture is prevented by storing I-BOND[®] OSB FC 4312 in carefully sealed containers under a dry air atmosphere.

During handling, the product must be protected from water ingress and from atmospheric moisture. Containers should be re-sealed immediately after each sampling. The reaction of isocyanates with water leads to the formation of insoluble urea's and carbon dioxide gas, which can lead to pressure build-up in closed containers. Containers used for

I-BOND[®] OSB FC 4312 must therefore be absolutely dry. The precautions necessary when handling I-BOND[®] OSB FC 4312 i.e. MDI, and the decontamination procedures recommended to be used in case of spillage, are described fully in the publication PU 193-1E; MDI-based compositions: Hazards and safe-handling procedures.

HEALTH AND SAFETY

The appropriate health and safety advice can be found in the safety data sheet for I-BOND[®] OSB FC 4312, available on request. The applicable Safety Data Sheet should be reviewed by customer before handling the Huntsman product. All users of I-BOND[®] OSB FC 4312 are advised to read the publication PU 193-1E; MDI-based compositions: Hazards and safe-handling procedures.

For further information, please contact your nearest sales office: http://www.huntsman.com/PU_customer_service

Warranty: Huntsman Polyurethanes warrants only that its products meet the specifications agreed with the buyer. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications. The manufacture of polyurethane materials and polymeric foams is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication. While all the information and recommendations in this publication are, to the best of our knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE, IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE. The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Polyurethanes. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof. Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Polyurethanes containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards. Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users. Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman International LLC or of its affiliated companies. Huntsman Polyurethanes is an international business unit of Huntsman International LLC. Huntsman Polyurethanes trades through Huntsman affiliated companies in different countries such as Huntsman International LLC in the USA and Huntsman Holland BV in Western Europe. I-BOND is a registered trademark of Huntsman LLC or an affiliate thereof, in one or more countries, but not all countries. Copyright © 2004 Huntsman LLC or an affiliate thereof. All rights reserved